




FIG. 1

11





CONDITION	DAY	PRIOR ART FLOORING BACKER	MELAMINE/ PHENOLIC BACKER	
ROOM	0	0.35	-0.69	
90% R.H. 72° F	1	0.81	-0.03	
	2	0.79	-0.06	
	3	0.92	-0.13	
	4	0.79		
	5			
	6		-0.16	
	7	0.83	-0.19	
10% R.H. 72° F	8	0.31	-1.38	
	9	-0.06	-1.38	
	10	-0.05	-1.38	
	11	-0.10		
	12			
	13		-1.44	
	14	-0.16	-1.38	
RANGE OF MOTION		PRIOR ART FLOORING BACKER	MELAMINE/ PHENOLIC BACKER	
		MAXIMUM	0.92	-0.03
		MINIMUM	-0.16	-1.44

FIG. 5




FIG. 6A




FIG. 6B